

## Window Graphics

### Perforated - Interior & Exterior Mount

Window graphics draw attention and generate increased store traffic. Pressure-sensitive solutions must be easy to install, they must stay adhered over a wide-range of temperatures, allow for bold, vivid graphics that resist fading and yellowing, and be simple to remove with no adhesive residue.

End-Use Applications:  
Perforated Window Graphics

For more information on FLEXcon's pressure-sensitive film solutions for Window Graphics, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX009136



This image is an example of how FLEXcon products may be used

#### Product:

**SEETHRU-SIGN® STSWBF7030**

#### Benefits:

- 7.2 mil perforated white/black flexible vinyl offers superior conformability to curved surfaces
- 70/30 vinyl perforation pattern yields 70% material for optimal viewing of the printed image
- 70/30 pattern yields 30% light transmission
- Offers visibility from the inside looking out with only limited visibility from the outside looking in
- Excellent printability via Solvent Screen, UV Inkjet, Solvent Inkjet and UV Screen
- HP Latex compatible\*
- Removable pressure-sensitive acrylic adhesive bonds well to smooth glass surface while removing cleanly
- Adhesive adheres well to an exterior glass surface over a wide range of temperatures
- Excellent layflat release liner properties for printing and converting
- Product is suitable for exterior mounted window graphics
- Approved and specified by JC Decaux for bus shelters
- Approved and specified by Titan for non-vehicle advertising

Please note: This product is not intended for sheet-form offset.

\*For more information on HP Latex compatibility, visit: [HP's Media Locator](#).

#### Recommendations:

Please refer to the "[Application Configuration Guidelines](#)" and the "[WindowGraphics Installation Guide](#)" for more information.



## SEETHRU-SIGN® STSWBF7030

PRODUCT DATA	VALUE	TEST METHOD
<b>Physical Properties</b>		
Thickness (Mils[microns])	Laminate	7.2 (183) +/- 15%
	Adhesive	0.8-0.9 (20-23) +/- 0.1 (3)
	Liner	7.5 (191) +/- 15%
Dimensional Stability (%)	MD	0.40
	TD	0.40
<b>Adhesion Properties</b>		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In	(N/m)
	Acrylic	16.0 (176)
	Glass	13.0 (143)
	Polypropylene	4.60 (51)
Stainless Steel	12.0 (132)	
<b>Expected Shear</b>		ASTM D 3654 Method A
		a. 1 hr. dwell
		b. 1 sq. in. surface
		c. 4 lb. load
Room Temp (hours)	0.10	
Tack (gm/sq cm)	130	ASTM D 2979
Expected Exterior Life	Two years	
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	40°F (4.5°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

### Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 12/04/2015

